

# VICAPROOF-200®

Edition 11020

## Highly Flexible, Two Component, Waterproofing Cementitious Slurry

### Description

**Vicaproof-200** is a Two component, highly flexible waterproofing slurry for concrete and masonry based on a blend of Portland cement & Vicat special binders, siliceous graded fillers, additives (part A) and modified acrylic polymer (part B). After mixing part A with part B it will produce workable slurry that can be applied by brush or trowel. **Vicaproof-200** complies with the requirements of standard: **EN 14891** as Liquid-applied water impermeable product class **CM01P**.

### Advantages

- Highly flexible with excellent crack bridging abilities
- Very low capillary absorption with good breathability.
- Resists carbonation providing excellent protection to steel reinforcement.
- Formulated for short and long term efficiency.
- Suitable for food industry and potable water.
- Excellent adhesion.
- Doesn't need surface smoothing before application.
- Can be used indoor and outdoor.
- Economic and easy to apply
- UV resistant.

### Uses

**Vicaproof-200** is ideal to be used for the following operations:

- To protect concrete against concrete decay providing a chemical resistant barrier to corrosive salts and atmospheric gases.
- Waterproofing of water retaining structures such as swimming pools and water tanks.
- Flexible waterproofing of Balconies & Roofs
- Acts a protective coating against moisture for foundations and wet areas.
- To provide protection to concrete surfaces from carbonation and chloride attack.

### Standards & Specifications

Color	Grey - beige -White
Toxicity	Non-toxic
Pot life	40mins at 24° C
Fresh density(by Brush)	1.7 Kg/liter
Tensile Adhesion to concrete substrate	≥1.5 N/mm <sup>2</sup>
Drying Time	≈ 120 mins at 24° C
Substrate temperature	+5 ° C to +35 ° C
Mixing ratio	25kg powder (Part A) : 10kg liquid polymer (Part B)
Crack bridging abilities: EN 14891 - A.8	Unreinforced: ≥ 3.00 mm Under standard conditions
Elongation at break: ASTM D412	≥ 60 % Under standard conditions
Tensile Strength:	≥ 1.0 Mpa
E-modulus:	≥ 10 Mpa
Impermeability to water, expressed as capillary absorption (kg/m <sup>2</sup> ·h <sup>0.5</sup> ): EN 1062-3	≤ 0,1 kg/m <sup>2</sup> · h <sup>0.5</sup>
Impermeability to water under pressure 5.0 bar for 7 days of positive lift: EN 14891-A.7	No penetration

## Package & Coverage

**Vicaproof-200** is supplied in a group of 25kg bag (Part A) + 10Kg liquid polymer (Part B).

After mixing Part A with Part B, the 35 Kg yields about 20 liters of slurry.

The rate of consumption is 1.5 - 2.0 kg/m<sup>2</sup> for two perpendicular applied coats depending on the substrate.

The minimum number of coats is two coats; additional coats may be required for high hydrostatic pressures.

Allowance should be made for any possible wastage when estimating. Various colors are available for large orders.

## Application Instructions

### **Surface preparation:**

All substrates should be clean, free from dust, loose particles, grease, oil or any other foreigner matter.

All concrete surface defects (Honey combs, Rock pockets, air voids .....etc.) should be repaired following a proper repair procedure, using **Vicaseal Mortar** or **Vicarep**. Before applying **Vicaproof-200**, all surfaces should be saturated with water with no running water (saturated surface dry).

### **Mixing:**

- In a suitable container add  $\frac{3}{4}$  the quantity of the liquid (part B) and Start mixing with a slow speed drill (350 - 450) rpm.
- While mixing, gradually add the powder (part A) and continue mixing to get rid of any lumps.
- Add the rest of the liquid (part B) and continue mixing until the slurry is homogeneous.

### **Application:**

- The slurry will be applied to the prepared SSD surfaces using a suitable brush at the rate of at least two perpendicular coats with a rate of consumption of 0.75 to 1.0 kg/m<sup>2</sup> for the single coat.
- Apply the second coat as soon as the previous one is dry enough to receive it (about 2-6hrs depending on temperature and humidity).
- Additional coats are optional and depend on the water head and substrate conditions.
- The final coat can be smoothed using a trowel after painting.
- When reinforcing is required, Coated Fiber Glass Mesh is embedded between the first two coats (Refer to our technical office).

### **Precautions:**

- Protect the **Vicaproof-200** bags (part A) from direct sun rays or any other source of heat before use, this can lead to a very fast setting. Protect the liquid (part B) from frost.
- Never apply more than 3kg/m<sup>2</sup> for one layer.
- Avoid working on hot substrates.
- Under any circumstances, never re-temper with water.
- Protect the freshly applied material from frost and rain until totally dry.
- After application, **Vicaproof-200** should be allowed to self-cure for at least 2 days before any water contact.
- **Vicaproof-200** must be protected from direct sun light and excessive wind.
- **Clean the used tools immediately with water before the material hardens.**

## Health and safety

**Vicaproof-200** is alkaline and should not come into contact with skin or eyes. Avoid inhalation of dust during mixing and wear safety glasses, dust mask and gloves. If skin contact occurs, wash thoroughly with clean water. Should eye contact occur, rinse immediately with plenty of clean water and seek medical advice.

## Storage & shelf life

**Vicaproof-200** should be stored in normal temperature and closed shaded dry area in undamaged original packing. It is recommended to be re-tested after 6 months from the production date.

## Technical support

For any technical support, please consult our technical office or representatives.  
Check our website for the latest version of the Technical Datasheet.

Disclaimer...The information contained herein is included for illustrative purpose only and, to the best of our knowledge, is accurate and reliable. Hemts cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As Hemts has no control over the use to which may put its products, it is recommended that the products be tested to determine if suitable for a specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine suitability of products for specific application and assume all responsibilities in connection therewith.

Hemts Construction Chemicals Ltd.

Head quarter: 35 ElGazayer St. 11435 Maadi, Cairo, Egypt  
Factory: CPC industrial compound, 6th of October, Giza, Egypt  
Tel: (+202)27030503 - 27542745 - 25180578 info@hemts.net

[www.hemts.net](http://www.hemts.net)

