

VICAGROUT-100®

Edition 10022

One component, shrinkage compensating, Flowable cementitious grout.

Description

VicagROUT-100 is a shrinkage compensated cementitious grout based on a blend of Portland cement, graded siliceous fillers and additives. **VicagROUT-100** has a controlled expansion feature to compensate any further shrinkage in plastic state. **VicagROUT-100** is mainly designed to fill confined voids and under base plates. The material is preblended and ready to be mixed with water to produce an easily placed grout.

Advantages

- Shrinkage compensated
- Increased strength due to the hydration process and lower water / cement ratio.
- Low permeability resists carbonation providing excellent protection to steel.
- Nontoxic & Suitable for food industry and potable water.
- No plastic settlement or bleeding.
- Good Air release.
- Excellent adhesion.
- Easy to use.
- Chloride free.

Uses

VicagROUT-100 can be easily used to fill voids and gaps between concrete or masonry elements, or between underneath base plates of steel columns or machines. The consistency should be adjusted from fluid to plastic depending on the type of application. Typical applications include but are not limited to:

- Grouting cable ducts in post tensioned concrete.
- Under-plate grouting.
- Underpinning.
- Infill concrete.
- Jointing precast units.
- Shrinkage compensated repair mixes.

Technical characteristics

Color

Grey (other colors are available upon request)

Setting time @ 23° C

	Plastic	Flowable	Fluid
Initial	30 min.	1hr 30min	3hr 00min
Final	45 min.	3hr 00min	4hr 00min

Toxicity

Non-toxic

Dry density

1.7 Kg/L

Fresh density (Fluid consistency)

2.2 Kg/L

Maximum Particle size

3 mm

Adhesion to concrete substrate

(Adhesion depends very much on proper surface preparation)

> 1 N/mm²

Flow according to BS EN 1015-3 (Without Jolting)

> 30Cm

Plastic Expansion ASTM C940

≈ 2.0 % at standard conditions

Flexural strength 28d EN 196-1:2005 (MPa) (Flowable)

> 10 MPa

Compressive strength tested according to EN 196-1:2005 (MPa). (4x4x16 prisms)

Consistency	Water/Powder ratio	Age		
		24 hours	7 days	28 days
Fluid	0.120	25	40	≥ 60
Flowable	0.100	30	50	≥ 70
Plastic	0.80	40	60	70-80

Package & Yield

VicagROUT-100 is supplied in 30 Kg bags.

After mixing with water, the 30 Kg bag yields about 15 liters of grout when mixing water per bag is 3.75 liter. Allowance should be made for any possible wastage or surface unevenness when estimating.

Application Instructions

Surface preparation

All substrates should be clean, free from dust, loose particles, grease, oil or any other foreigner matter. Formwork should be erected and made grout-tight. The formwork must be designed with sufficient hydrostatic head to ensure grout flow into and across the grouting area. Saturate the grouting area with water, check for leaks, leave for one hour and then blow out any surplus water. All concrete surfaces should be surface saturated dry (SSD) just before the application.

Mixing

Pour about 3.0 – 3.75 liters of clean water into the mixing vessel for each complete 30 kg bag of **VicagROUT-101**. Slowly add the **VicagROUT-100** to the water whilst continually mixing for 3 - 5 minutes. Mechanical mixing is essential using either a high torque slow speed drill with a Grout Stirrer or a grout mixer set on a slow speed. (High speed or colloidal mixing will cause thixotropy leading to loss of flow). Hand mixing is not recommended.

Application

Grout should be placed before the gelling time to insure good flowability; otherwise slight vibration could overcome the problem. Continuous placing is important, pouring from one side of the formwork until the grout appears at the opposite side of the grouting area. Do not disturb once grouting has been completed. The grout is chloride-free, can be safely used in contact with steel and can be placed in section thicknesses of 10mm up to 50mm. To take full advantage of the expansion properties **VicagROUT-100** should be applied within maximum 20 minutes from mixing.

Curing

Immediately after placing the grout, all exposed areas should be covered with clean wet hessian and kept moist until grout surface is ready to be finished, or until final set. After final setting, continue the curing process with soaking, wet hessian or a curing compound.

Precautions

Protect the **VicagROUT-100** bags from direct sun rays or any other source of heat before use; this can lead to a very fast setting. Avoid working on hot substrates and avoid mixing with hot water, the temperature of both the grout and elements coming into contact with the grout should be in the range of +5°C to +35°C. Never exceed the stated water dose and temperature to avoid bleeding, segregation and further cracking. Never remix with water to retrieve its initial workability. For application thickness other than the stated, please refer to our technical office.

Avoid contact with gypsum or any other sulfates on substrate, mixing water or curing water in plastic state.

Health and safety

VicagROUT-100 is alkaline when mixed with water and should not come into contact with skin or eyes. Avoid inhalation of dust during mixing and wear safety glasses, dust mask and gloves. If skin contact occurs, wash thoroughly with clean water. Should eye contact occur, rinse immediately with plenty of clean water and seek medical advice. Full health and safety data are given in Product Safety Data Sheet.

Storage & shelf life

VicagROUT-100 should be stored in normal temperature and closed shaded dry area in undamaged original packing. It is recommended to be re-tested after 6 months from the production date if packed in paper bags and retested after 18 months if packed in plastic bags.

Technical support

For any technical support, please consult our technical office or representatives.

Disclaimer...The information contained herein is included for illustrative purpose only and, to the best of our knowledge, is accurate and reliable. HEMTS cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As HEMTS has no control over the use to which may put its products, it is recommended that the products be tested to determine if suitable for a specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine suitability of products for specific application and assume all responsibilities in connection therewith.

Hemts Construction Chemicals Ltd.

Head quarter: 35 ElGazayer St. 11435 Maadi, Cairo, Egypt
Factory: CPC industrial compound, 6th of October, Giza, Egypt
Tel: (+202)27030503 - 27542745 - 25180578 info@hemts.net

www.hemts.net

